

TEST REPORT

ADODDITIVES TECHNOLOGIES PVT.LTD.
D-1, ACHARYA NIKETAN
MAYUR VIHAR, PHASE-1
DELHI-110091, DELHI
INDIA

Phone/Fax:
Kind Attn. : ASHA

Report No.: 161103069-1

Sample Description :
CURING COMPOUND (AT CURE WR125W)

Date: 08-Nov-2016
DOR: 03-Nov-2016

Your Ref. No. :

ID. No. 161103069-1

Date of start of Testing:- 03.11.2016
Date of Completion of Testing:-08.11.2016

CURING COMPOUND (AT Cure WR125W)

S.No.	Test Parameters	Observed Results	Test Methods	Requirements as per ASTM C 309	Conformity
1	Water Retention, Kg/m ² in 72 hrs.	0.48	ASTM C 156	0.55 Max.	Yes
2	Specific Gravity	1.090	ASTM D 1475	-----	-----
3	Drying Time at 23±2°C, Minute	88	ASTM C 309	4 hr. Max.	Yes
5	pH Value	10.26	By pH Meter	-----	-----
6	Coverage, Kg/m ²	0.092	As per ASTM C 309	-----	-----

-----End of Test Report-----



Analyst *[Signature]*

CCREQD\2\RA000\IA6900

[Signature]
P.K. TIWARI
MANAGER
Authorised Signatory

TRA - 266126